

## M22759/5 to /12 • Extruded PTFE Insulation

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/5	VA	Silver	Extruded PTFE*	200°C	600 V	24 to 20
M22759/6	WA	Nickel	Extruded PTFE*	260°C	600 V	24 to 20
M22759/7	SA	Silver	Extruded PTFE*	200°C	600 V	24 to 8
M22759/8	TA	Nickel	Extruded PTFE*	260°C	600 V	24 to 8
M22759/9	LE	Silver	Extruded PTFE	200°C	1000 V	28 to 10
M22759/10	LH	Nickel	Extruded PTFE	260°C	1000 V	28 to 8
M22759/11	RC	Silver	Extruded PTFE	200°C	600 V	28 to 8
M22759/12	RE	Nickel	Extruded PTFE	260°C	600 V	28 to 8

\* Denotes mineral filled PTFE insulation

## M22759/13 to /15 • Extruded FEP Insulation, with PVDF outer

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/13	CA	Tin	Extruded FEP/PVDF	135°C	600 V	24 to 10
M22759/14	CB	Tin	Extruded FEP/PVDF	135°C	600 V	26 to 12
M22759/15	CC	Silver HSCA	Extruded FEP/PVDF	135°C	600 V	26 to 20

## M22759/16 to /19 • Extruded ETFE Insulation

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/16	TE	Tin	Extruded ETFE	150°C	600 V	24 to 00
M22759/17	TF	Silver HSCA	Extruded ETFE	150°C	600 V	26 to 20
M22759/18	TG	Tin	Extruded ETFE	150°C	600 V	26 to 10
M22759/19	TH	Silver HSCA	Extruded ETFE	150°C	600 V	26 to 20

## M22759/20 to /31 • Extruded PTFE Insulation

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/20	TK	Silver HSCA	Extruded PTFE	200°C	1000 V	28 to 20
M22759/21	TL	Nickel HSCA	Extruded PTFE	260°C	1000 V	28 to 20
M22759/22	TM	Silver HSCA	Extruded PTFE	200°C	600 V	28 to 20
M22759/23	TN	Nickel HSCA	Extruded PTFE	260°C	600 V	28 to 20
M22759/28	JB	Silver	Extruded PTFE/Polyimide	200°C	600 V	28 to 10
M22759/29	JC	Nickel	Extruded PTFE/Polyimide	260°C	600 V	28 to 10
M22759/30	JD	Silver HSCA	Extruded PTFE/Polyimide	200°C	600 V	28 to 20
M22759/31	JE	Nickel HSCA	Extruded PTFE/Polyimide	260°C	600 V	28 to 10

## M22759/32 to /46 • Extruded XL-ETFE Insulation

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/32	SB	Tin	Extruded XL-ETFE	150°C	600 V	30 to 12
M22759/33	SC	Silver HSCA	Extruded XL-ETFE	200°C	600 V	30 to 20
M22759/34	SD	Tin	Extruded XL-ETFE Dual Wall*	150°C	600 V	24 to 00
M22759/35	SE	Silver HSCA	Extruded XL-ETFE Dual Wall	200°C	600 V	26 to 20
M22759/41	SD	Nickel	Extruded XL-ETFE Dual Wall*	200°C	600 V	26 to 00
M22759/42	SN	Nickel HSCA	Extruded XL-ETFE Dual Wall	200°C	600 V	26 to 20
M22759/43	SD	Silver	Extruded XL-ETFE Dual Wall*	200°C	600 V	26 to 00
M22759/44	SR	Silver	Extruded XL-ETFE	200°C	600 V	28 to 12
M22759/45	SS	Nickel	Extruded XL-ETFE	200°C	600 V	28 to 12
M22759/46	ST	Nickel HSCA	Extruded XL-ETFE	200°C	600 V	28 to 20

\* Denotes polymeric braid as outer sheath on certain sizes

## M22759/80 to /92 • Composite Taped Wires

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/80	WB	Tin	Fluoropolymer/Polyimide, 2 Ply	150°C	600 V	26 to 10
M22759/81	WC	Silver, HSCA	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 20
M22759/82	WE	Nickel, HSCA	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 20
M22759/83	WF	Silver	Fluoropolymer/Polyimide, 4 Ply*	200°C	600 V	2 to 0000
M22759/84	WG	Nickel	Fluoropolymer/Polyimide, 4 Ply*	260°C	600 V	2 to 0000
M22759/85	WH	Tin	Fluoropolymer/Polyimide, 4 Ply*	150°C	600 V	2 to 0000
M22759/86	WJ	Silver	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/87	WK	Nickel	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/88	WL	Tin	Fluoropolymer/Polyimide, 2 Ply	150°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/89	WM	Silver HSCA	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 20
M22759/90	WN	Nickel HSCA	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 20
M22759/91	WP	Silver	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 10
M22759/92	WR	Nickel	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 10

\* Denotes polymeric braid as outer sheath

## M22759/180 to /192 • Composite Taped Wires, Smooth

Reference	M27500 Identifier	Conductor Plating	Insulation	Temp. Rating	Voltage Rating	AWG
M22759/180	DB	Tin	Fluoropolymer/Polyimide, 2 Ply	150°C	600 V	26 to 10
M22759/181	DC	Silver, HSCA	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 20
M22759/182	DE	Nickel, HSCA	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 20
M22759/183	DF	Silver	Fluoropolymer/Polyimide, 4 Ply*	200°C	600 V	2 to 0000
M22759/184	DG	Nickel	Fluoropolymer/Polyimide, 4 Ply*	260°C	600 V	2 to 0000
M22759/185	DH	Tin	Fluoropolymer/Polyimide, 4 Ply*	150°C	600 V	2 to 0000
M22759/186	DJ	Silver	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/187	DK	Nickel	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/188	DL	Tin	Fluoropolymer/Polyimide, 2 Ply	150°C	600 V	26 to 10
			Fluoropolymer/Polyimide, 3 Ply			8 to 6
			Fluoropolymer/Polyimide, 4 Ply			4 to 0000
M22759/189	DM	Silver, HSCA	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 20
M22759/190	DN	Nickel, HSCA	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 20
M22759/191	DP	Silver	Fluoropolymer/Polyimide, 2 Ply	200°C	600 V	26 to 10
M22759/192	DR	Nickel	Fluoropolymer/Polyimide, 2 Ply	260°C	600 V	26 to 10